

EX-2C Clear 100

Endura EX-2C Clear 100 is a clear coating designed to give extra protection to solid, metallic, and pearl colors. It is suitable for use in many harsh chemical environments, providing extra protection against the effects of acid and acid rain. UV light absorbers provide exceptional ultraviolet light protection and increase the service life of all colors.

Product Features

- ◆ Excellent protection against acids and alkalis
- ◆ Exceptional ultraviolet light protection
- ◆ Exceptional abrasion resistance
- ◆ A durable, self-prime coating for wood floors

Theoretical Solids Content:

Volume: 38%

Shelf Life*

Component A: (3) years
Component B: (1) year

*For unopened product.

Pot Life of Mixed Product:

8-10 Hours* @ 77°F (25°C) and 50% RH

* Less when Endura Super Catalyst II is used.



Suitability**

Endura EX-2C Clear 100 is suitable for protecting most finished surfaces including solid colors, metallic and pearl colors. **For flexible surfaces such as aircraft fabric or rubber, use EX-2C Clear 100 SFC as recommended. On projects that require recoatability please use EX-2C Midcoat Clear 100.** The performance enhancing additives of EX-2C Clear 100 interfere with recoatability of this product. Fish eyes or cratering is likely.



Surface Preparation

Ensure that surfaces to be clear coated are free of flaws, surface contaminants and other imperfections. If the surface has been allowed to cure longer than 24 hours, sanding will be required to achieve intercoat adhesion. Sand topcoat lightly with 600 grit sandpaper or 3M White Scuff Pads. **Do not sand Metallic or Pearl colors. Do not mix Clear 100 with color for final coat.**



Mixing Ratio


1 part by volume of component A [CLRTB100]
1 part by volume of component B [FUB0100]
The recommended temperature when mixed is 20-25°C (68-77°F).

Environmental Conditions

For optimum coating performance product, substrate and ambient temperature should be between 20°C-25°C* (68°F-77°F). To prevent condensation during application the surface temperature must be 3°C (5°F) or more above the dew point at all times.
*for use outside this range please contact your Endura representative.



Spraying Viscosity*




* Spraying viscosity and thinning will depend on ambient conditions, spray equipment used, and on the desired surface finish.
If required, recommended spraying viscosity is achieved by reducing with Endura Topcoat Reducers.



Spray Gun Setup

Feed Type	Fluid Tip	Application Pressures (heel of gun)	Fluid Delivery
Siphon Feed	1.6-1.8 mm	40-50 psi	
Gravity Feed	1.3-1.8 mm	30-40 psi	
Pressure Feed	1.0-1.4 mm	55-65 psi	10-14 oz/min
Air Assist Airless	9-13 Thou	1,000-1,800 psi	
Airless	11-13 Thou	1,700-3,000 psi	



EX-2C Clear 100

Endura EX-2C Clear 100 is a clear coating designed to give extra protection to solid, metallic, and pearl colors. It is suitable for use in many harsh chemical environments, providing extra protection against the effects of acid and acid rain. UV light absorbers provide exceptional ultraviolet light protection and increase the service life of all colors.

Product Features

- ◆ Excellent protection against acids and alkalies
- ◆ Exceptional ultraviolet light protection
- ◆ Exceptional abrasion resistance
- ◆ A durable, self-prime coating for wood floors

Theoretical Solids Content:

Volume: 38%

Shelf Life*


Component A: (3) years
Component B: (1) year

*For unopened product.

Pot Life of Mixed Product:

8-10 Hours* @ 77°F (25°C) and 50% RH

* Less when Endura Super Catalyst II is used.



Endura Clear 100
EX-2C Topcoat
Endura Sealer**
Endura Primer
Substrate

**optional

Application Method

Clear coats can be applied as soon as the surface has cured enough to wipe with a tack cloth. Apply two wet coats with 30 - 60 minutes between coats. EX-2C Topcoats require a drying time of 8 - 10 hours before application of EX-2C Clear 100. Drying time can be reduced with accelerator*.

Recommended Film Build Thickness and Cover Rate

Endura EX-2C Clear 100 has a recommended film thickness of:

Wet (unreduced): 2.5 – 5.0 mils wet (67.5 – 125 microns)

Dry: 1.0 - 2.0 mils dry (25 – 50 microns).

Theoretical coverage at 1.0 mil (25 microns) DFT: 608 ft² per gallon @ 100% transfer efficiency.

Drying Time*

For recoatability please use EX-2C clear 100 (recoatable)

* Please note that the use of Super Catalyst II with Endura topcoats will accelerate drying times.

	20°C (68°F)	30°C (86°F)	40°C (104°F)
Dust Free	2 Hours	1 Hour	30 Minutes
Full Cure	7-14 Days		

* Subject to ambient conditions (temperature and humidity) film build and good airflow. For improved scheduling please contact your Endura representative.

Specifications

Hardness	ASTM D3363	4H
Solvent resistance	ASTM D4752	100 MEK rubs; NO failure
Abrasion resistance (1000 cycles CS-17)	ASTM D4060	25 mg loss
Impact resistance	ASTM D2794	80 in. lbs; NO failure
Flexibility	ASTM D522	1/8" mandrel bend; NO failure
VOC	For VOC amounts please refer to the product MSDS	

Clean Up

Endura high strength gun wash, Endura epoxy reducer or Endura EX-2C thinner.