

Guardian

Endura Guardian is a, low VOC, high solids, semi-gloss coating, that is surface tolerant providing good adhesion to damp surfaces.

Product Features

- ◆ Excellent water resistance
- ◆ Low temperature cure to 0°F (-18°C)
- ◆ Suitable for salt & fresh water immersion
- ◆ Excellent adhesion to tight rust
- ◆ Abrasion & chemical resistance is excellent
- ◆ High solids (high film build)
- ◆ No induction time

Theoretical Solids Content:

Volume: 68%


Shelf Life*

Component A: (3) years
Component B: (1) year

*For unopened product.

Pot Life of Mixed Product:

4.5 Hours @ 77°F (25°C) and 50% RH



Suitability

Endura Guardian is suitable for use on properly prepared steel, aluminum or masonry surfaces including immersion (non-potable water) service. Endura Guardian can also be used as an intermediate coat.



Surface Preparation

Commercial sandblasting or machine sanding with 40 grit sandpaper is acceptable for most applications.

For Aluminum surfaces:

- 1) acid etch; i.e. Endura Neutralizer 20, Endura Aluminum Cleaner, etc... or use
- 2) Endura MetaLink



Mixing Ratio

4 parts by volume of part A
1 part by volume of part B [FEB0111]

The recommended temperature when mixed is 20-25°C (68-77°F).


Environmental Conditions

For optimum coating performance product, substrate and ambient temperature should be between 20°C-25°C* (68°F-77°F). To prevent condensation during application the surface temperature must be 3°C (5°F) or more above the dew point at all times.

*for use outside this range please contact your Endura representative.



Spraying Viscosity



If required, recommended spraying viscosity is achieved by reducing with Endura HAPS free/low VOC thinner.



Spray Gun Setup

Feed Type	Fluid Tip	Application Pressures (heel of gun)	Fluid Delivery
Siphon Feed	1.6-2.0 mm	40-50 psi	
Gravity Feed	1.3-1.4 mm	30-40 psi	
Pressure Feed	1.0-1.8 mm	50-60 psi	10-14 oz/min
Air Assist Airless	9-17 Thou	1,000-1,800 psi	
Airless	11-13 Thou	1,700-3000 psi	

Guardian

Endura Guardian is a, low VOC, high solids, semi-gloss coating, that is surface tolerant providing good adhesion to damp surfaces.

Product Features

- ◆ Excellent water resistance
- ◆ Low temperature cure to 0°F (-18°C)
- ◆ Suitable for salt & fresh water immersion
- ◆ Excellent adhesion to tight rust
- ◆ Abrasion & chemical resistance is excellent
- ◆ High solids (high film build)
- ◆ No induction time

Theoretical Solids Content:

Volume: 68%

Shelf Life*

Component A: (3) years
Component B: (1) year

*For unopened product.

Pot Life of Mixed Product:

4.5 Hours @ 77°F (25°C) and 50% RH



Recommended Film Build Thickness and Cover Rate

Endura Guardian has a recommended film build thickness of 4.0-8.0 mils (100-200 microns) DFT.

Theoretical coverage at 1.0 mil (25 microns) dry: 1088 ft² per gallon @ 100% transfer efficiency.



Drying Time*

	20°C (68 °F)	30°C (86°F)	40°C (104°F)
Min. Recoat (5 mils)	6-10 Hours	5 Hours	3 Hours
Max. Recoat (self)	7 Days		
Max. Recoat (EX2C)	7 Days		
Full cure	7-9 Days	5-6 Days	3-4 Days

* Subject to ambient conditions (temperature and humidity) and good airflow. For improved scheduling please contact your Endura representative.

Specifications

Solvent Resistance	ASTM D4752	50 MEK rubs: NO Failure
Impact resistance	ASTM D2794	40 in.lbs: NO Failure
service temperature range**	-40°C to +121°C	-40°F to 250°F



Clean Up

Endura high strength gun wash, Endura epoxy reducer or Endura EX-2C thinner.

Notes

Limitations of use: Exterior exposure will cause a color change, early dulling, and loss of gloss, but this does not affect protection properties. GUARDIAN is commonly finished with ENDURA EX2C topcoats for maximum exterior color & gloss retention. **Do not use for fuel or solvent immersion.**

