


Spot test using 37% hydrochloric acid (highest concentration of Muriatic acid) for 72 hours under watch glass. All coatings were applied on steel panels without epoxy primer.



	DuraCoat	EX-2C	Jones Blair
2 Hours	Not Affected	Not Affected	Not Affected
5 Hours	Not Affected	Not Affected	Blistered
10 Hours	Not Affected	Blistered	Blistered
24 hours	Not Affected	Blistered	Blistered
72 Hours	Blistered	Blistered	Blistered