

### ① Product & Substrate Temperature




25°C (77°F)  
20°C (68°F)

20-25 °C (68-77 °F)\*



### ② Product Preparation



3 Part Component A  
1 Part Component B



### ③ Mixing



Paint must be thoroughly mixed.

### ④ Spraying Viscosity



As necessary\*\*

23 seconds\*\*

conventional

airless

**Viscosity: 23 seconds/as necessary using a Ford 4 Cup (white)**

\*\* Spraying viscosity and thinning will depend on ambient conditions, spray equipment used, and on the desired surface finish.



### ⑤ Spray Gun Setup




Feed Type	Fluid Tip	Application Pressure	Fluid Delivery
Siphon Feed	1.6-1.8 mm	40-50 psi	
Gravity Feed	1.6-1.8 mm	30-40 psi	
Pressure Feed	1.4-1.8 mm	50-60 psi	10-14 oz/min
Air Assist Airless	9-17 Thou	1000-1800 psi	
Airless	13-17 Thou	1700-3000 psi	



### ⑥ Application

Recommended Film Thickness



5.0 - 10.0 mils wet



4.0 - 8.0 mils DFT